



CODE **THETALENE-R H3 GF30I09CC NA1000**

DESCRIPTION *PP HOMO 30%GF CC NATURAL*

REV 01

ISSUED 18/03/2021

PROPERTIES	UNITS	VALUE - DAM		METHOD
PHISICAL				
SPECIFIC GRAVITY	g/cm ³	1.13		ISO 1183
MELT FLOW INDEX (230°C - 2,16 Kg)	g/10'	10-15		ISO 1133
MOISTURE ABSORPTION 24h at 23° in H2O*	%	-		INTERNAL
MOISTURE ABSORPTION saturation*	%	-		INTERNAL
MOULDING SHRINKAGE: ALONG FLOW*	%	0,2-0,4		INTERNAL
MOULDING SHRINKAGE: ACROSS FLOW*	%	0,7-0,9		INTERNAL
MECHANICAL				
TENSILE STRENGHT*	MPa	80		ISO 527-2
TENSILE MODULUS*	MPa	6000		ISO 527-2
ELONGATION AT BREAK at 23°C *	%	3		ISO 527-1
FLEXURAL STRENGHT*	MPa	120		ISO 178
FLEXURAL MODULUS*	MPa	5700		ISO 178
IZOD IMPACT STRENGHT NOTCHED 23°C	KJ/m ²	9		ISO 180/A
THERMIC				
VICAT/B (50N; 120° C/h)	°C	130		ISO 306
HDT/A (1,8 Mpa)	°C	145		ISO 75-2
FLAMMABILITY				
FLAME RATING (1,6 mm – 3,2 mm)	CLASS	HB		UL 94
GLOW WIRE FLAMMABILITY INDEX (1 mm)	°C	-		IEC 60695-2-12
PROCESSING				
PREDRYING TEMPERATURE	°C	40	60	
PREDRYING TEMPERATURE TIME	h	2	3	
RECOMMENDED MELT TEMPERATURE	°C	210	260	

Compound di polipropilene (PP) riciclato realizzato con la percentuale minima del 30% derivante da scarti post-industriali (PIR) della linea commerciale THETALENE R.

Recycled polypropylene (PP) compound obtained from post-industrial waste in the minimum quantity of 30%, named THETALENE R.



This document is propriety of Powerpol s.r.l. and can't be used without our autorization. Values in this data sheet are only indicatives, they are not product specifications. We cannot forecast every conditions where our informations and our products will be used, then we can't guarantee applicability fitness for a specific use. For this reason we decline any responsibility for damage to customers and others.

* : values only indicative, they aren't product specifications and aren't checked by our quality system.